

TU.BR.CREMA MARFIL

| | |
|-----------|--------------|
| FORMAT | 60x60 |
| THICKNESS | 9.500 |
| PRODUCT | |
| TYPE | GL Esmaltado |
| GROUP | Bib |

APPLICABLE STANDARD EN 14411 ANNEX G



| TESTS | | RESULTS | |
|-------|---|--|----------------------------|
| | UNE-EN ISO 10545-2 DIMENSIONAL FEATURES | COMPLIES WITH THE STANDARD | |
| | UNE-EN ISO 10545-3 WATER ABSORPTION | 0,5 % - 3 % | |
| | UNE-EN ISO 10545-4 MODULUS OF RUPTURE | BREAKING STRENGTH | >1300 N |
| | | BENDING STRENGTH | >35 N/mm2 |
| | UNE-EN ISO 10545-7 RESISTANCE TO SURFACE ABRASION | - | |
| | UNE-EN ISO 10545-8 LINEAR THERMAL EXPANSION | <7,0 x 10 ⁻⁶ °C ⁻¹ | |
| | UNE-EN ISO 10545-9 THERMAL SHOCK RESISTANCE | RESISTS | |
| | UNE-EN ISO 10545-11 CRAZING RESISTANCE | RESISTS | |
| | UNE-EN ISO 10545-12 FROST RESISTANCE | RESISTS | |
| | UNE-EN ISO 10545-13 CHEMICAL RESISTANCE | AMMONIUM CHLORIDE 100 G/L | A |
| | | SODIUM HYPOCHLORITE 20 MG/L | A |
| | | HYDROCHLORIC ACID 3% | COMPLIES WITH THE STANDARD |
| | | CITRIC ACID 100 G/L | COMPLIES WITH THE STANDARD |
| | | POTASSIUM HYDROXYDE 30 G/L | COMPLIES WITH THE STANDARD |
| | UNE-EN ISO 10545-14 STAIN RESISTANCE | GREEN AGENT IN LIGHT OIL | 5 |
| | | IODINE SOLUTION IN ALCOHOL | 5 |
| | | OLIVE OIL | 5 |
| | UNE 41901:2017 EX SLIP RESISTANCE (PENDULUM) | - | |
| | DIN 51130 CRITICAL ANGLE OF SLIP (INCLINED PLATFORM) | - | |
| | DIN 51097 CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS | - | |
| | (PTV) DRY CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) DRY | - | |
| | BS7976 (PTV) WET CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET | - | |
| | ANSI A326.3 DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS. | - | |